



Alfa Laval Installation Material

Alfa Laval is your complete source for specialized fittings and tubing required in food, dairy, beverage, personal care, biotechnology and pharmaceutical process applications. Smooth, crevice-free interiors and secure, self-aligning joints are characteristic for Alfa Laval Fittings. Each offers superior corrosion-resistance and unmatched service life. Alfa Laval fittings are designed and manufactured to ensure dimensional accuracy and structural integrity, making them easy to install. Tubing is manufactured to Alfa Laval's stringent specifications, making it a perfect match for the weld fittings. Choose from a wide range of tube sizes, surface finishes and connect options. All products are labelled with a bar code, product information and manufacturing date. This provides the optimum identification and ensures that the product arrives to the job site in a clean orbital weld condition.

The Alfa Laval tubes and fittings are divided into two product ranges, Hygienic and UltraPure, The Hygienic range is suitable for most standard duties and the UltraPure range is suitable for duties with extra high demands on hygiene and cleanability.

Hygienic range tubes and fittings

The Hygienic product range offers a wide range of tubes and fittings with an internal surface finish from $Ra < 0.8 \mu\text{m}$ to $Ra < 1.6 \mu\text{m}$. The Hygienic range has tubes and fittings according to EN10357-A (DIN 11850), ISO 2037, BS 4825 and ASME BPE dimension standards.

UltraPure range tubes and fittings

The UltraPure product range offers a wide range of tubes and fittings with an internal surface finish from $Ra < 0.4 \mu\text{m}$ to $Ra < 0.8 \mu\text{m}$, either electro polished or mechanically polished. The UltraPure range has tubes and fittings according to ASME BPE dimension standard. The UltraPure range is manufactured in compliance with the ASME BPE standard. All tubes and fittings are internally cleaned and individually capped and bagged. All product wetted stainless steel products in the UltraPure range are delivered with MTR (Mill Test Report) or with 3.1. certificate in accordance to EN 10204.

The UltraPure range is manufactured under extra strict and thorough quality control methods. Wall thickness integrity is maintained through the use of fabrication grade minimum wall tubing for all cold-formed tubular products. After cold forming, our tube product is resized to ensure that the ovality falls within the prescribed tolerances. End facing is provided with a machined square-cut method. This allows for the most accurate and consistent orbital weld result. All fittings are put through 100% visual inspection and ovality and squareness tolerances are inspected with calibrated equipment. Surface finish is inspected with a calibrated profilometer to ensure the Roughness average (Ra) maximum is not exceeded.



Surface specification for Alfa Laval Hygienic range

Hygienic tubes

Alfa Laval designation	Surface texture (Ra μm)			Standard designation	According to	Treatment	EN 10357-A	Dimension ranges		Tri-Clover® Hygienic
	Internal Surface	Welded area	External					ISO 2037	BS 4825	
BC	< 0.8	< 1.6	pickled	BC	EN 10357-A	Annealed	X	X	X	
BD	< 0.8	< 1.6	< 1.0	BD	EN 10357-A	Annealed	X	X	X	
CC	< 0.8	< 1.6	pickled	CC	EN 10357-A	Not annealed	X			
CD	< 0.8	< 1.6	< 1.0	CD	EN 10357-A	Not annealed	X			
Tri-Clover® Hygienic	< 0.8	< 0.8	< 0.8	No. 4 ¹⁾	3A	Annealed				X

1) According to 3A 33-01 section D1

Hygienic Fittings

Product	Surface designation		DIN	ISO	Dimension ranges BS	Tri-Clover® Hygienic
	Internal	External				
Unions	Mat	Mat	X			
	Semi bright	Semi bright	X	X	X	
	Mirror	Mirror				
	3A	3A				X
Bends	Mat	Mat	X			
	Raw	Raw			X	
	Raw	Semi bright	X			
	Raw	Polished	X	X		
	Semi bright	Semi bright		X		
	Polished	Polished			X	
	Mirror	Mirror				
Tees	3A	3A				X
	Mat	Mat	X			
	Raw	Raw			X	
	Polished	Polished	X	X	X	
	Mirror	Mirror				
Reducers	3A	3A				X
	Mat	Mat	X			
	Raw	Semi bright	X			
	Raw	Polished		X	X	
	Semi bright	Semi bright		X		

Explanation of surface designation for fittings

Alfa Laval designation	Surface texture (Ra μm)		Method
	Internal	Bended area	
Mat	< 1.6	Not spec.	Shot Blasted
Raw	< 0.8 ¹⁾	Not spec.	As fabricated or tumbled
Semi bright	< 0.8	Not spec.	As fabricated or tumbled
Polished	< 0.8	Not spec.	Mechanically polished
Mirror	< 0.8	Not spec.	Mechanically polished and buffed for a shiny surface
3A	< 0.8	< 0.8	Mechanically polished or as fabricated

¹⁾ Not guaranteed in welds.

Surface specification for Alfa Laval Tri-Clover® UltraPure range
UltraPure tubes and fittings

Alfa Laval designation	Surface texture (Ra μm)			Standard designation		According to	Treatment	Tri-Clover® UltraPure ASME-BPE
	Internal	Welded / Bended area	External	Tubular	Machined			
PL	< 0.5	< 0.5	< 0.8	SF1	SF1	ASME BPE	Annealed	X
PM	< 0.4 EP ³⁾	< 0.4 EP ³⁾	< 0.8	SF4	SF4	ASME BPE	Annealed	X

³⁾ Electro polished

* SF-Surface Finish. SF4: Ra < 0.375 EP

Conversion table - Surface finish

Correlation between Grit and Ra values

Ra (μm)	Ra (μ inch)	US Grit	UK Grit
3	125		120
2	85		180
1.65	70	80	
1.5	50		240
0.75	30		320
0.62	25	180	
0.45	18	240	
0.40	15		500
0.25	10	320	

Material specification for Alfa Laval Hygienic range

Wetted steel parts

Material	Dimension ranges			
	EN 10357-A	ISO 2037	BS 4825	Tri-Clover® Hygienic
1.4301* (304)	X	X		
1.4307* (304L)	X	X	X	
1.4401* (316)			1)	
1.4404* (316L)	X	X	X	
304**				X
316L**				X

1) Reducing tees are only available in 1.4401 (316)

* According to DIN EN 10088-1

** According to ASTM A 269 and A 270.

Seal ring material for clamp fittings

Material	Dimension ranges			
	EN 10357-A	ISO 2037	BS 4825	Tri-Clover® Hygienic
NBR	X	X	X	
Nitrile (Buna-N)				X
White Nitrile (White Buna-N)				X
EPDM	X	X	X	X
FPM	X	X	X	
Viton®				X
PTFE	X	X	X	X
Silicone (Q)	X	X		X

Material specification for Alfa Laval Tri-Clover® UltraPure range

Wetted steel parts

Material	Dimension ranges
	Tri-Clover® UltraPure
	ASME-BPE
316L*	X

* According to ASTM A 269 and A 270 S2. All Tri-Clover® UltraPure ASME BPE weld ends are also according to ASME BPE sulphur content 0.005-0.017%

Gasket material in fittings

Material	Dimension ranges
	Tri-Clover® UltraPure
	ASME-BPE
Nitrile (Buna-N)	X
White Nitrile (White Buna-N)	X
EPDM	X ¹⁾
FPM	
Viton®	X ¹⁾
White Viton®	X
PTFE	X
Silicone (Q)	X ¹⁾

¹⁾ EPDM, Viton and Silicone available with USP Class 6 certificate - please request by order.

Chemical composition table

Material Grade		C	Si	Mn	Chemical composition in % by mass					
Material	Standard				P	S	N	Cr	Ni	Mo
1.4404	DIN-EN 10088-1	≤ 0.030	≤ 1.000	≤ 2.00	0.045	≤ 0.015	≤ 0.11	16.50 - 18.50	10.00 - 13.00	2.00 - 2.50
316L	ASTM A 269	≤ 0.035	≤ 0.750	≤ 2.00	0.040	≤ 0.030		16.00 - 18.00	10.00 - 15.00	2.00 - 3.00
316L*	ASTM BPE / ASTM A 270 S-2	≤ 0.035	≤ 0.075	≤ 2.00	0.040	0.005 - 0.017		16.00 - 18.00	10.00 - 10.00	2.00 - 3.00

*According to ASTM A 269 and A 270 S2. All Tri-Clover® UltraPure ASME BPE weld ends are also according to ASME BPE sulphur content 0.005-0.017%

Pressure ratings (bar) for Alfa Laval Hygienic range

Material	Dimension ranges			
	DIN	SMS / ISO 2037	BS 4825	Tri-Clover® Hygienic
Tubes (20°C)	39/355	39/355	56-467*	56-351*
Bends, Tees, Reducers (80/200°C)	40/16	40/16	25/15	25/15
Nut unions (80/200°C)	40/16	40/16	25/15	
Flange unions (80/200°C)	25/16	25/16	25/15	

* Tube pressure ratings depending on size (larger diameter smaller pressure rating)



Pressure ratings (bar) of Tri-Clamp® Connections

Size Tube OD	Service Ratings* (bar)						
	1/2 & 3/4 inch	1 & 1 1/2 inch	2 inch	2 1/2 inch	3 inch	4 inch	6 inch
13MHLA (Screw tightened to maximum)							
at at 20°C	--	10.3	10.3	10.3	10.3	10.3	--
at at 120°C	--	8.6	8.6	8.6	8.6	5.2	--
13MHHM (Wing nut tightened to 2.8 Nm of torque)							
at at 20°C	--	34.5	31.0	27.6	24.1	20.7	10.3
at at 120°C	--	20.7	20.7	13.8	13.4	10.3	5.2
13MHHS (Wing nut tightened to 2.8 Nm of torque)							
at at 20°C	151.7	41.4	37.9	31.0	24.1	20.7	--
at at 120°C	82.7	20.7	19.0	15.5	12.1	10.3	--
13MHP (Bolts tightened to 2.71 Nm of torque)							
at at 20°C	--	103	68.9	68.9	68.9	55.1	20.7
at at 120°C	--	82.7	55.2	55.2	55.2	41.4	13.8
A13MO (1-3" nuts tightened to 2.3 Nm, 4-6" 3.4 Nm of torque)							
at at 20°C	--	34.5	24.1	20.7	13.8	10.3	5.2
at at 120°C	--	17.2	13.8	10.3	10.3	10.3	3.4
A13MHM (Wing nut tightened to 2.8 Nm of torque)							
at at 20°C	--	34.5	31	27.6	24.1	20.7	10.3
at at 120°C	--	20.7	17.2	13.8	12.1	10.3	5.2

* Service ratings are based on hydrostatic tests using standard-molded Buna-N material gaskets, with proper installation of ferrules, assembly of joints and absence of shock pressure.

All ratings shown are dependent upon related components within the systems and proper installation. For temperatures above at 120°C, we recommend using only 13MHP clamps.

Pressure drop and flow velocity curves



Alfa Laval reserves the right to change specifications without prior notification.

How to contact Alfa Laval

Contact details for all countries
are continually updated on our website.
Please visit www.alfalaval.com to
access the information direct.